

AS 2000

Synergestic Blend of MoS₂ and Friction Modifiers



YOUR BENEFITS

- Excellent lubrication property.
- Low co-efficient of friction.
- Anti-galling and Anti-fretting.
- Non-magnetic.
- Excellent anti-seizing property.
- 7 Good resistance to acids, oxidation, solvents, chemicals, washout.
- 7 Can be used as a dry lubricant under vacuum and radiation.
- Very high yield point and high load carrying capacity.
- → Wide range operating temperature band of (-)185°C to (+)450°C.

APPLICATION

- 7 As a dry lubricant for smooth surfaces.
- Press fits, punching, stamping and cold or warm forging.
- 7 For relays and switches, shrink fits, swaging, deep drawing, forging, extruding, packing. For V-belts, 'O' rings and sleeve bearings.
- → As an antiseize for thread lubricants.

CHARACTERISTICS	TEST METHOD	UNIT	TECHNICAL VALUES
Appearance	Visual	-	Fine powder
Colour	Visual	-	Greyish black
Bulk Density	*CTM	gms/ltrs	200 – 300
Particle Size [avg.]	*CTM	Micron	. ≤5
Friction Value [approx.]	-	-	0.04
Operating Temperature Range	-	°C	-185/+450

CTM:-Corporate Test Method

The values quoted above are typical and do not constitute a specification.

INDUSTRY:

Forging

PACK SIZE:

2 kg / 10 Kg Bucket

SHELF LIFE:

24 Months

Marginal variation in shade can be expected from batch to batch. The color has no effect on the lubricating properties of the product. MSDS available on request. Due to continual upgradation of products above data is subject to change without notice.

This supersedes our previously issued data sheets.

Information and data given herein is offered in good faith as accurate, but without guarantee. Conditions of use and suitability of a product for a particular use is beyond our control; all risks of use of the product are assumed by the user and WE EXPRESSLY DISCLAIM ALL WAR RANTIES OF EVERY KIND AND NATURE.

