

Safol FGG

NSF, HALAL & KOSHER Certified Food Grade Grease



YOUR BENEFITS

- 7 NSF H-1, HALAL & KOSHER Certified.
- → Non-toxic.
- 7 Tasteless and does not affect food quality in case of incidental contact.
- Good sealing capacity and resistance to loads.
- Guards against corrosion.
- Resistance to hot and cold water.
- Wide band operating temperature range.

APPLICATION

- 7 For bearing/sliding parts in processing, filling and sealing machines.
- 7 For lubrication of rubber or plastic moving parts under wet conditions.
- For rubber protection.
- 7 For lubrication of valve, stems, glands & plugs in food carrying pipelines.
- As a release agent on gaskets & seals in food and pharmaceutical machinery.

APPROVALS

NSF Registration No.: 155685, 161809, 161810

Halal: HIW25670318Kosher: AND1625KCJ





Safol FGG

NSF, HALAL & KOSHER Certified Food Grade Grease



| CHARACTERISTICS | TEST METHOD | UNIT | #2 | #1 | #0 |
|-----------------------------|-------------|--------|----------------------|----------------------|----------------------|
| Appearance | Visual | - | Smooth | Smooth | Smooth |
| Colour | Visual | - : | White | White | White |
| Base [Thickener] | - | - | Aluminium Complex | Aluminium Complex | Aluminium Complex |
| Base Oil | - | - | Synthetic | Synthetic | Synthetic |
| Base Oil Viscosity @ 40°C | ASTM D 445 | cSt | 200 | 200 | 200 |
| Flash Point (of Base Oil) | ASTM D 92 | °C | +220 | +220 | +220 |
| NLGI Grade | - | - | #2 | #1 | #0 |
| Penetration @ 25°C | ASTM D 217 | 0.1 mm | 265-295 | 310-340 | 355-385 |
| Dropping Point | ASTM D 2265 | °C | +270 | +260 | NA |
| Four Ball Weld Load | ASTM D 2596 | Kgs | 200 | 200 | 200 |
| Copper Strip Corrosion Test | ASTM D 4048 | Rating | la | la | Та |
| Operating Temperature Range | - | °C | -30/+180 | -30/+180 | -30/+180 |

INDUSTRY:

Animal Feed, Sugar

PACK SIZE:

 $1 \, \text{Kg} \, / \, 5 \, \text{Kg} \, / \, 20 \, \text{kg Bucket}$ 180 kg Drum

SHELF LIFE:

24 Months

The values quoted above are typical and do not constitute a specification.

Marginal variation in shade can be expected from batch to batch. The color has no effect on the lubricating properties of the product. MSDS available on request. Due to continual upgradation of products above data is subject to change without notice.

This supersedes our previously issued data sheets.

Information and data given herein is offered in good faith as accurate, but without guarantee. Conditions of use and suitability of a product for a particular use is beyond our control; all risks of use of the product are assumed by the user and WE EXPRESSLY DISCLAIM ALL WAR RANTIES OF EVERY KIND AND NATURE.