

Ultratack Mill Grease 460

High Viscosity Calcium Sulphonate Grease for Steel & Paper Mills

YOUR BENEFITS

- ↗ Suitable over wide temperature range.
- ↗ Excellent water resistance.
- High load carrying capacity.
- Excellent shear stability.
- High drop point.
- Excellent anti-wear properties.
- Contains no lead or other harmful matter.

APPLICATION

- Work Roll & Backup roll bearings in steel mills.
- 7 Heavily loaded bearings paper mills which come in contact with water.

CHARACTERISTICS	TEST METHOD	UNIT	TECHNICAL VALUES
Appearance / Colour	Visual	-	Smooth / Black
Base (Thickener)	-	-	Calcium Sulphonate Complex
Base Oil	-	-	Mineral
Base Oil Viscosity @40°C	ASTM D 445	cSt	460
NLGI Grade	-	-	#2
Worked Penetration	ASTM D 217	0.1 mm	265 - 295
Dropping Point	ASTM D 2265	°C	+300
Four Ball Weld Load	ASTM D 2596	Kgs	400
Copper Strip Corrosion Test	ASTM D 4048	Rating	la
Water Washout @80°C, wt loss	ASTM D 1264	%	< 0.45
Oil Separation @100°C / 24hr	ASTM D 6184	%	0.17
Roll Stability Change	ASTM D 1831	%	< 5
Operating Temperature Range	-	°C	- 20/+200

INDUSTRY:

Steel

PACK SIZE:

1 Kg / 5 Kg / 20 Kg Bucket 180 Kg Drum

SHELF LIFE:

24 Months

The values quoted above are typical and do not constitute a specification.

This supersedes our previously issued data sheets.

Information and data given herein is offered in good faith as accurate, but without guarantee. Conditions of use and suitability of a product for a particular use is beyond our control; all risks of use of the product are assumed by the user and WE EXPRESSLY DISCLAIM ALL WAR RANTIES OF EVERY KIND AND NATURE.

Anand Engineers Pvt Ltd 66, MIDC, Road No.13, Andheri East, Mumbai 400093. MH, India. W : www.molygraph.com E : sales@molygraph.com M : +91 81044 09925

Page 1 Edition 13.05.19



Marginal variation in shade can be expected from batch to batch. The color has no effect on the lubricating properties of the product. MSDS available on request. Due to continual upgradation of products above data is subject to change without notice.